





Stock Range					
	450x640	520x720	640x900	720x1020	1020x720
208g/m ² / 350µm	✓	✓	✓	✓	
235g/m ² / 400µm	✓	✓	✓	✓	✓
260g/m ² / 456µm	✓	✓	✓	✓	✓
280g/m ² / 499µm	✓	✓	✓	✓	✓
320g/m ² / 587µm	✓	✓	✓	✓	✓

CERTIFICATIONS				
				
FSC®	ISO 9001	ISO 14001	ISEGA	Carbon Balanced

denmaur 
A CARBON BALANCED COMPANY

www.denmaur.com



Weight	Thickness	Bulk	Stiffness		Brightness		
			g/m ²	µm	cm ³ /g	Taber 15° mNm	Top
				MD	CD	%	%
190*	305	1.61	5.4	2.8	≥ 90	≥ 90	
208	350	1.68	10.0	5.1	≥ 90	≥ 90	
225*	390	1.72	13.4	6.6	≥ 90	≥ 90	
235	400	1.70	-	-	≥ 90	≥ 90	
240*	425	1.77	16.9	8.5	≥ 90	≥ 90	
260	455	1.75	21.1	10.5	≥ 90	≥ 90	
280	500	1.78	25.6	12.8	≥ 90	≥ 90	
300*	540	1.80	30.9	15.4	≥ 90	≥ 90	
320	585	1.83	36.7	18.4	≥ 90	≥ 90	
340	635	1.86	43.3	21.6	≥ 90	≥ 90	
+/- 4%	+/- 5%						
Tolerances							

* Only available mill direct and subject to minimum order quantities