



revive™ Digital Silk

Stock Range

g/m ²	320 x 460	460 x 320*
115	✓	
130	✓	
150	✓	
170	✓	
200		✓
250		✓
300		✓
350		✓

* short grain

Technical Specifications

Weight	g/m ²	90*	100*	115	130	150	170	200	250	300	350
Thickness	µm	70	77	88	100	115	134	162	207	261	315
Bulk	ISO 534 cm ³ /g	0.78	0.77	0.77	0.77	0.77	0.79	0.81	0.83	0.87	0.9
Brightness	ISO 2470 %	96	96	96	96	96	96	96	96	96	96
Smoothness	ISO 5627 s	500	500	500	450	400	350	300	200	150	100
Opacity	ISO 2471 %	92.5	94	95	96	97	98min	98min	98min	98min	98min

* Please note that these weights are available on an ex-mill basis.



revive™ Digital Silk

Print Processes

Litho	Dry Toner Colour Digital*	HSWO **	CutStar **
✓	✓	✓	✓

* Compatible for most dry toner digital presses

** Available on an ex-mill basis

Finishing Suitability

Laminate	Spot UV	Varnish	Foil Block	Folding	Die Cut	Emboss	Scoring
✓	✓	✓	✓	✓	✓	✓	✓

Sustainability

Pulp		Environmental	Quality	Energy
FSC®	Recycled	ISO 14001	ISO 9001	ISO 50001
✓	✓	✓	✓	✓

FSC® Forest Stewardship Council® Forest management certification scheme

ISO 14001 International standard for environmental management

ISO 9001 International standard for quality management

ISO 50001 International standard for energy management

Updated and published : 23rd April 2019