



Temptation Velvet

(soft to the touch)

PRINT LAMINATION FILM

Available in Thermal and Digital

TEMPTATION Velvet is a polyurethane coated, biaxially oriented polypropylene film; the backside is coated with EVA hot melt. The EVA needs some time for optimal curing. The time for curing depends on the base material used and should be tested before further processing.

The thickness of the film is 30 μm ($\pm 5\%$); the film can be used for materials of various kinds. The optimum processing temperature of the laminating roll is between 100 °C and 115 °C.

FEATURES:

- Soft surface
- Ultra-matt surface
- Modified scuff resistance
- Good tear resistance
- Suitable for hot foil stamping (test required)
- Suitable for spot coatings with radical UV-curing system (test required)
- Glueable (test required/ tests were made on a folder gluing machine with water based glues)

THERMAL:

FILM TYPE:	Thermal Temptation Velvet
THICKNESS:	30 microns
YIELD:	38.80 m ² /kg
SURFACE TENSION:	40 dyne/cm
RUNNING TEMPERATURE:	100 to 115 °C

DIGITAL:

FILM TYPE:	Digital Temptation Velvet
THICKNESS:	30 microns
YIELD:	39.20 m ² /kg
SURFACE TENSION:	40 dyne/cm
RUNNING TEMPERATURE:	100 to 115 °C